

PATENT
3502-1003



IN THE U.S. PATENT AND TRADEMARK OFFICE

Applicant: Olof NORRLOW et al. Conf.:
Appl. No.: **NEW** Group:
Filed: January 28, 2002 Examiner:
For: METHOD FOR THE PREPARATION OF SODIUM
PERCARBONATE GRANULES HAVING ENHANCED
STABILITY

#2

CLAIM TO PRIORITY

Assistant Commissioner for Patents
Washington, DC 20231

January 28, 2002

Sir:

Applicant(s) herewith claim(s) the benefit of the
priority filing date of the following application(s) for the
above-entitled U.S. application under the provisions of 35
U.S.C. § 119 and 37 C.F.R. § 1.55:

<u>Country</u>	<u>Application No.</u>	<u>Filed</u>
FINLAND	20010164	January 26, 2001

Certified copy(ies) of the above-noted application(s)
is(are) attached hereto.

Respectfully submitted,

YOUNG & THOMPSON

Benoit Castel

Benoit Castel, Reg. No. 35,041

745 South 23rd Street
Arlington, VA 22202
Telephone (703) 521-2297

BC/ia

Attachment(s): 1 Certified Copy(ies)

PATENTTI- JA REKISTERIHALLITUS
NATIONAL BOARD OF PATENTS AND REGISTRATION

Helsinki 11.12.2001

ETUOIKEUSTODISTUS
PRIORITY DOCUMENT

10/056006
10/28/02
10971 U.S. PTO



Hakija
Applicant
Kemira Chemicals Oy
Helsinki

Patenttihakemus nro
Patent application no
20010164

Tekemispäivä
Filing date
26.01.2001


Kansainvälinen luokka
International class
C01D

Keksinnön nimitys
Title of invention

"Method for the preparation of sodium percarbonate granules having enhanced stability"
(Menetelmä parantuneen stabiliteetin omaavien natriumperkarbonaattirakeiden valmistamiseksi)

Täten todistetaan, että oheiset asiakirjat ovat tarkkoja jäljennöksiä patentti- ja rekisterihallitukselle alkuaan annetuista selityksestä, patenttivaatimuksista, tiivistelmästä ja piirustuksista.

This is to certify that the annexed documents are true copies of the description, claims, abstract and drawings originally filed with the Finnish Patent Office.


Pirjo Kalla
Tutkimussihteeri

Maksu 300 mk (50 € 1.1.2002 lähtien)
Fee 300 FIM (50 EUR from 1 January 2002)

Maksu perustuu kauppa- ja teollisuusministeriön antamaan asetukseen 1027/2001 Patentti- ja rekisterihallituksen maksullisista suoritteista muutoksineen.

The fee is based on the Decree with amendments of the Ministry of Trade and Industry No. 1027/2001 concerning the chargeable services of the National Board of Patents and Registration of Finland.

Osoite: Arkadiankatu 6 A Puhelin: 09 6939 500 Telefax: 09 6939 5328
P.O.Box 1160 Telephone: + 358 9 6939 500 Telefax: + 358 9 6939 5328
FIN-00101 Helsinki, FINLAND

Method for the preparation of sodium percarbonate granules having enhanced stability

5 This invention relates to a method for the preparation of sodium percarbonate granules wherein the granule surface is modified by creating a dense thin film enhancing the stability of the final sodium percarbonate product. Further, the invention relates to these stability enhanced sodium percarbonate granules, and to the use of these granules in detergent compositions.

10 Sodium percarbonate (SPC) is a water-soluble crystalline peroxygen compound with the molecular formula $2\text{Na}_2\text{CO}_3 \cdot 3\text{H}_2\text{O}_2$. Its theoretical active oxygen content (AO) is 15.28% by weight. Sodium percarbonate as such is a stable compound but it tends to decompose when included in detergent formulations, especially during storage, loosing its active oxygen content. The stability of a percarbonate compound in a detergent formulation is essential for the success of replacing perborate compounds
15 as peroxide bleaching sources.

Especially, entering a more severe climate requiring storage under very warm and/or humid conditions sodium percarbonate will decompose even alone. An other problem is the use of sodium percarbonate in zeolite-containing detergents where it looses its bleaching effect after a relatively short storing period.

20 The decomposition of sodium percarbonate can be prevented or delayed by coating the SPC granules. The use of thick sodium bicarbonate and other inorganic coating layers has been previously disclosed. It is also possible to use organic materials and polymers, and combinations of these different materials. It is also known to obtain more stable sodium percarbonate by screening a commercial product in a specific
25 manner for a certain particle size and form.

From thin film technology, it is known that even very thin films in order of 5-50 nm can be chemically very resistant depending on the material and the used technology. For example, etch barriers for wet lithographic processes can be formed in which the thin layers are of better quality, much denser and chemically more resistant, than
30 the corresponding bulk material. A typical issue is to obtain rather a thin conformal coating than a thick mechanically protective layer. This is especially true when rough surfaces or sharp steps are to be covered and protected. This type of conformal coating is preferably pinhole free thus showing good chemical resistance towards e.g. aqueous solutions.

A similar assumption was applied to the preparation of a thin coating film onto the surface of a spherical and in a microscopic scale rough SPC granule. The morphological studies have shown that the surface roughness of an SPC granule produced in a special fluidized bed reactor is not very high only about one micrometer which is less than the roughness obtained by several other preparation methods. This enhances the possibility to influence and modify the surface microstructure in a more uniform manner.

In our previous patent EP 861 557 the surface of sodium percarbonate granules was first sprayed with water in order to dissolve a minor fraction of the sodium percarbonate granule surface. Subsequently, the dissolved aqueous sodium percarbonate surface layer formed was neutralised into a thin layer of sodium bicarbonate by carbon dioxide gas. In this method the carbon dioxide gas was introduced onto the surface as part of the fluidizing gas used in a fluidized bed reactor. As the water film dries in the presence of carbon dioxide gas a thin sodium bicarbonate layer remains on the granule surface. The granules thus prepared could be coated with other coating materials to form a thick additional coating layer. These sodium percarbonate granules were used in zeolite-containing detergents and in humid air conditions these granules exhibited better stability characteristics than granules prepared without the deposition of the thin bicarbonate layer. The measured results showed indirectly the influence of the SPC surface modification.

Presently, the stability of percarbonate is at an adequate level but entering even more severe climate than usual, storage under warm and humid conditions together with a zeolite-containing detergent a further improved product is needed. Thus, the method described in our previous patent EP 861 557 was developed further.

The object of the invention is to improve the formation conditions of the thin protective bicarbonate film and this is accomplished by using carbon dioxide gas dissolved in water prior to application onto the sodium percarbonate granules. By treating the surface using carbon dioxide gas dissolved in water a better quality thin film is achieved judged indirectly by the stability experiments made using this method compared to otherwise prepared products.

Hence this invention provides a way to further enhance the stability of sodium percarbonate granules by optimising the formation conditions of the thin sodium bicarbonate film onto the surface of the sodium percarbonate granules.

Thus, in one aspect of the invention there is provided a method for the preparation of sodium percarbonate granules having enhanced stability, comprising modifying the surface of the sodium percarbonate granules by means of a surface reaction between sodium percarbonate and carbon dioxide or bicarbonate species to form a
5 dense solid film of essentially sodium bicarbonate on the surface of the sodium percarbonate granules, said method comprising the steps of:

- a) dissolving carbon dioxide in water to form an aqueous solution containing dissolved carbon dioxide and bicarbonate,
- b) exposing the surface of the sodium percarbonate granules to a spray of said
10 aqueous solution containing dissolved carbon dioxide and bicarbonate, to form said solid film of essentially sodium bicarbonate, and subsequently
- c) removing the residual fluid from the surface.

Preferred embodiments of the method of the invention are described in claims 2 to 10.

- 15 In a second aspect of the present invention there is provided sodium percarbonate granules prepared by the method of the invention.

According to present invention CO_2 can be dissolved into water a spray by using a conventional two-way nozzle. Preferably, driving air of the spray nozzle containing from 0.2 to 5% by weight CO_2 is sprayed through one nozzle and this gas mixture is
20 dissolved into water which is sprayed through the other nozzle. A spray of water saturated with CO_2 is directed towards the SPC granules and these granules reside in the fluidized bed preferably for 0.5 to 15 min. For example, air can be used as the fluidizing gas stream. The temperature in the fluid bed is maintained between 30°C and 90°C by electrically controlled heating elements. The granule surface is
25 modified by the thin bicarbonate film formed by the reaction of moisture and CO_2 or HCO_3 with SPC. After this the thin surface film is dried.

Further, according to the present invention CO_2 can be dissolved into water in a separate premixing tank before guiding the solution into the fluid bed and exposing the SPC granules residing in the bed to the spray. This type of premixing allows the
30 dissolution more time and the ambient conditions can be more easily regulated.

Additionally, according to the present invention CO_2 can be dissolved into water inside the guiding line ending at the fluid bed by static mixing. Water and CO_2 gas are injected into the guiding line before the fluid enters the fluid bed. This type of solution is mechanically the easiest to realize.

An additional coating layer can be deposited on top of this modified surface or intermediate film. The additional coating layer is formed by spraying an aqueous solution from a spray nozzle onto the granules having the intermediate film already on, preferably in the fluidized bed. After the additional coating the product is ready to be used for example as a detergent component.

In one embodiment of the invention the surface modification by CO_2 is performed several times meaning that the above steps a) to c) are repeated from 1 to 10 times, in order to enhance the influence of the surface modification by making the thin bi-carbonate film thicker. The thickness of the formed thin film depends on the number of coating sequences used. Accurate thickness measurements from the used SPC surfaces are very difficult to perform but the film thickness is estimated to be less than 100 nm.

In another embodiment of the invention the water saturated with carbon dioxide can be prepared by dissolving carbon dioxide in water at an elevated pressure to enhance the gas content and to speed up the dissolution.

The content of CO_2 , calculated as percent by weight of the sprayed substances, in the water to be sprayed on the surfaces of the SPC granules is preferably at least 0.25%, more preferably at least 0.5%.

The fluidizing gas used can be for example air, N_2 or any other inert gas, preferably air.

The solution for spraying the additional coating layer can comprise various materials commonly used for coating e.g. sodium bicarbonate, soda (including the various forms of sodium carbonate), sodium sulphate, a mixture of lithium sulphate and sodium sulphate, a mixture of soda and sodium sulphate or a polymer with or without a metal sulphate.

Preferably, the additional coating layer comprises from 1 to 20% by weight, and more preferably from 5 to 12% by weight of the sodium percarbonate granule.

The present invention decreases considerably the CO_2 consumption of the process compared to the method described in our previous patent EP 861 557. The CO_2 purge is now concentrated on the location where it directly can be dissolved into the used water and in a more efficient form carried into contact with the SPC granule surface. This design reduces the amount of CO_2 by more than 90%. In addition, the

SPC granule surface confronts an enhanced amount of dissolved CO_2 or the concentration of H_2CO_3 or HCO_3^- in the water is locally higher.

In addition, the temperature and pH of the aqueous solution to be applied to the granules is easier to adjust making the process more robust.

- 5 The stability of the product when prepared by the above described method of the present invention is enhanced by about 10%. The mechanism behind the phenomenon is not quite clear. It is possible that due to the formed thin film of sodium bicarbonate the adherence and thus the quality of the additional coating layer is enhanced.
- 10 The invention is described in more detail by following examples. The enclosed Figures 1 and 2 show graphically the stability results from comparative tests.

Example 1

SPC granules were prepared using a fluid bed spray granulator as described in Kemira Kemi's production brochure "ECOX Sodium percarbonate" from 9/98.

- 15 These uncoated SPC granules with a mean granule diameter of 0.7 mm were circulated back into the processing chamber of the granulator. The fluidization gas was air with a velocity of $120 \text{ m}^3/\text{h}$. A two-way nozzle was used in Glatt AGT 150 fluid bed apparatus for coating the SPC granules. The bed temperature was essentially 60°C .

- 20 The CO_2 -enriched fluid spray was prepared by spraying CO_2 -enriched air from one nozzle used as driving gas with a gas pressure of 0.15 MPa (1.5 bar) and gas flow of $5.6 \text{ m}^3/\text{h}$. This flow was dissolved in water which was sprayed from the second nozzle at the rate of 40 g/min.

- 25 By exposing the SPC granules to the CO_2 enriched fluid spray for 2 min, the granules were coated by a thin bicarbonate surface film.

Example 2

The amount of carbon dioxide in the driving gas to be dissolved in water was varied. The contents of 0%, 0.25%, 0.5% and 1% were used and the coating was carried out as described in example 1.

- 30 Subsequently, the bicarbonate-coated granules were sprayed with a sodium sulphate solution to form a sodium sulphate coating in an amount of 10% by weight of the

SPC granules. This additional coating layer was sprayed using the same nozzle as for coating with CO₂, after the CO₂ coating. Air was used as driving gas.

The SPC granules thus treated were mixed with zeolite in a weight ratio of 50/50 for testing the stability in the presence of detergent conditions.

- 5 The samples were positioned in open boxes into a humidity chamber at a temperature of 30°C and 70% relative humidity for 12 weeks. The active oxygen values were measured before and after the test and the amount of decomposition was calculated from the peroxide content determined by titration before and after storage. The test results are compiled in Table 1.

10 **Table 1**

Amount of CO ₂ (%)	Decomposition in (%)
0	70
0.25	65
0.5	53
1.0	48

The above results show a clear decrease in the decomposition as the carbon dioxide content in the spraying fluid was increased.

Example 3

- 15 SPC granules were prepared according to example 1 by using 0% and 0.5% of CO₂ in the driving gas. These granules were coated further and mixed into a detergent base according to example 2. Both detergent mixtures were filled into detergent cartridges and closed hermetically. These two cartridges were placed into a climate chamber for 8 weeks at 40°C and 70% RH.
- 20 The reference sample with 0% of CO₂ coating showed 41% of decomposition and in the sample coated with 0.5% CO₂ in the driving gas the decomposition was halved, 22%.

Example 4

- 25 SPC granules were coated as described in examples 1 and 2 using 1% CO₂ in the driving air of the nozzle and two minutes of spraying with the CO₂-containing water.

Subsequently, the bicarbonate-coated granules were sprayed with a sodium sulphate solution to form a sodium sulphate coating in an amount of 12% by weight of the SPC granules.

5 In a control test uncoated SPC granules were sprayed with a sodium sulphate solution to form a sodium sulphate coating in an amount of 12% by weight of the SPC granules.

The SPC granules had a size distribution between 0.50-0.71 mm. The decomposition of the granules was tested at 30°C temperature and 70% relative humidity for 12 weeks as described in example 2.

10 The decomposition curves are shown in figure 1. The results show that the thin bicarbonate film formed on the surfaces of the SPC granules decreased decomposition by 25%.

Example 5

15 SPC granules were coated using CO₂ by the method described in EP 861 557 and according to examples 1 and 2 above using 1.0% CO₂ in the driving air of the nozzle and 2 minutes of spraying with the CO₂-containing water.

Subsequently, the bicarbonate-coated granules were sprayed with a sodium sulphate solution to form a sodium sulphate coating in an amount of 9% by weight of the SPC granules.

20 The decomposition of the coated granules was tested at 30°C temperature and 70% relative humidity for 12 weeks as described in example 2.

The decomposition curves are shown in figure 2. The results show that the decomposition percentage decreases further by 8 units in the SPC granules prepared according to the method of the present invention.

25 Example 6

The coating of the SPC granules were realized by introducing carbon dioxide gas into a pH adjusted water solution in a separate mixing tank, before guiding this solution into the sprayer. The pH values of the tank solutions were adjusted by addition of appropriate amounts of NaOH. Experiments were carried out with initial
30 pH values of the water solutions being 8, 9 and 11. The diameter of the SPC granules used in these experiments was 0.7 mm. Water solutions were purged with

60 l/h CO₂ gas flow for 7 min, 5 min and 6 min, respectively, before introduction onto the SPC granules in the fluid bed.

5 After coating the granules with CO₂ containing water solution, the granules were additionally coated with sodium sulfate (NAS) from Säteri Factories. Table 2 shows the influence of the premixing in tank and adjustment of the solution pH in terms of NAS and H₂O₂ percentage of the stabilized product and its decomposition rate.

Table 2

Initial pH	NAS (%)	H ₂ O ₂ (%)	Decomposition rate (%)
8	10.7	28.1	35.5
9	10.2	28.3	32.3
11	10.7	28.2	29.6

Claims

1. A method for the preparation of sodium percarbonate granules having enhanced stability, comprising modifying the surface of the sodium percarbonate granules by means of a surface reaction between sodium percarbonate and carbon dioxide or bicarbonate species to form a dense solid film of essentially sodium bicarbonate on the surface of the sodium percarbonate granules, characterized in that
 - a) carbon dioxide is dissolved in water to form an aqueous solution containing dissolved carbon dioxide and bicarbonate,
 - b) the surface of the sodium percarbonate granules is exposed to a spray of said aqueous solution containing dissolved carbon dioxide and bicarbonate, to form said solid film of essentially sodium bicarbonate, and subsequently
 - c) the residual fluid is removed from the surface.
2. A method according to claim 1, characterized in that the carbon dioxide is dissolved in water in a two-way nozzle to form the spray of said aqueous solution containing dissolved carbon dioxide.
3. A method according to claim 1, characterized in that the carbon dioxide is dissolved in water in a premixing tank.
4. A method according to claim 1, characterized in that the carbon dioxide is dissolved in water inside a guiding line tube wherein the carbon dioxide gas and water are injected.
5. A method according to any of claims 1 to 4, characterized in that the content of carbon dioxide in the aqueous solution to be sprayed is at least 0.25% by weight.
6. A method according to any of claims 1 to 5, characterized in that the surface of the sodium percarbonate granules is exposed to said spray for a period of from 0.5 to 15 minutes.
7. A method according to any of claims 1 to 6, characterized in that the thickness of said film is less than 100 nm.
8. A method according to any of claims 1 to 7, characterized in that the method additionally comprises repeating steps a) to c) from one to ten times to increase the thickness of the film by creating multiple layers.

9. A method according to any of claims 1 to 8, characterized in that the method is carried out in a fluidized bed reactor comprising a step of spraying said aqueous solution containing dissolved carbon dioxide inside the fluidized bed from a spray nozzle inside the fluidized bed reactor.
- 5 10. A method according to any of claims 1 to 9, characterized in that the method additionally comprises depositing an additional coating layer on top of said film of sodium bicarbonate, said additional coating layer comprising sodium sulphate, soda, sodium bicarbonate, a mixture of sodium sulphate and lithium sulphate, a mixture of soda and sodium sulphate, a mixture of a metal sulphate and a polymer or a
10 polymer.
11. Sodium percarbonate granules prepared according to the method of any of claims 1 to 10.
12. Use of sodium percarbonate granules of claim 11 in detergents, especially in detergents containing zeolite.

(57) Abstract

The invention relates to a method for the preparation of sodium percarbonate granules having enhanced stability, comprising modifying the surface of the sodium percarbonate granules by means of a surface reaction between sodium percarbonate and carbon dioxide or bicarbonate species to form a dense solid film of essentially sodium bicarbonate on the surface of the sodium percarbonate granules, said method comprising the steps of:

- a) dissolving carbon dioxide in water to form an aqueous solution containing dissolved carbon dioxide and bicarbonate,
- b) exposing the surface of the sodium percarbonate granules to a spray of said aqueous solution containing dissolved carbon dioxide and bicarbonate, to form said solid film of essentially sodium bicarbonate, and subsequently
- c) removing the residual fluid from the surface.

L5




Figure 1




Figure 2